

Ask Jon Eakes

LOOSE FILL POURED: GLASS FIBER

Last Updated: Thursday, March 28th, 2013, Created: Thursday, October 14th, 1999

Same appearance and characteristics of Blown-in Glass Fiber except: Thermal Resistance: RSI - .021/mm R - 3.0/in. Fair Applications:-- Attics. Accessible enclosed cavities with great care and no obstructions. It gets hung up very easily.

Keywords:

R-Value, Types, Insulation

Article 800

www.joneakes.com