

Ask Jon Eakes

LOOSE FILL POURED: WOOD SHAVINGS

Last Updated: Thursday, March 28th, 2013, Created: Thursday, October 14th, 1999

Thermal Resistance: RSI - .017/mm R - 2.4/in. Low.Costs: Varies greatly but low.Capacity to dry out if wet: PoorFire Resistance: PoorFungus / Vermin Resistance: PoorLimitations: -- Quality varies considerably in both density, type and chemical additives. -- Settles too much for use in walls.Advantages: -- Cost.Applications: -- Attics.

Keywords:

R-Value, Types, Insulation

Article 805

www.joneakes.com