

Ask Jon Eakes

LOOSE FILL POURED: WOOD SHAVINGS

Last Updated: Friday, October 15th, 1999, Created: Friday, October 15th, 1999

Thermal Resistance: RSI - .017/mm R - 2.4/in. Low.

Costs: Varies greatly but low.

Capacity to dry out if wet: Poor

Fire Resistance: Poor

Fungus / Vermin Resistance: Poor

Limitations:

- Quality varies considerably in both density, type and chemical additives.
- Settles too much for use in walls.

Advantages:

- Cost.

Applications:

- Attics.

Keywords:

Insulation, R-Value, Types

Article 805
www.joneakes.com